



### DESIGNATION AND PROPERTIES:

- For marking of roads and highways, airplane tracks, parking areas, kindergarten areas and sport areas with asphalt and concrete pavement.
- Designed for city area working in heavy traffic.
- Long lasting of the white color.
- High resistance to abrasion and quick drying.
- Good elasticity.
- In compliance with EN 1871:2004.

### TECHNICAL PARAMETERS:

INDEXES	NORMS
Flowing time, funnel 6 mm, (23±0,5°C): (EN ISO 2431)	min 90 s
Density, (23±0,5°C): (EN ISO 2811-1)	min 1,65 kg/L
Non-volatile substances content (105-110)°C/1h/2g: (EN ISO 3251)	min 78 %
Complete drying time, (23±2)°C, In dry film thickness 45 - 60 µm: (EN 29117)	max 25 min
Sand abrasion to the film, in dry film thickness 60 µm: (BSS 14120-77)	0,82 kg/µm
Consumption:	450-550 kg/m <sup>2</sup> in dry film thickness 250 µm.
Packaging:	Metal packaging in net weight: 25/30 kg.

